



Processing Conditions

Nylon 6 (PA)

Typical Injection Molding Conditions

	English	SI Metric
Temperatures		
Rear zone	430 - 500 °F	221 - 260 °C
Center zone	450 - 510 °F	232 - 266 °C
Front zone	480 - 520 °F	249 - 271 °C
Melt	470 - 535 °F	243 - 279 °C
Mold	130 - 200 °F	54 - 93 °C
Pressures		
Injection	10000 - 15000 psi	69 - 103 MPa
Hold	4000 - 10000 psi	28 - 69 MPa
Back	50 - 100 psi	0.34 - 0.69 MPa
Speeds		
Fill	2 - 3 in/sec	51 - 76 mm/sec
Screw	60 - 90 rpm	60 - 90 rpm
Drying		
Time & Temperature	2 Hrs @ 175 °F	2 Hrs @ 79 °C
Dew Point	0.0 °F	-18 °C
Moisture Content	0.20 %	0.20 %